

Domex 500 MC

Hot rolled, extra high strength, cold forming steel

Product

Domex cold forming steels are thermo-mechanically rolled in modern plants where the heating, rolling and cooling processes are carefully controlled.

The chemical analysis, consisting of low levels of carbon and manganese has precise addition of grain refiners such as niobium, titanium or vanadium. This together with a clean structure, makes Domex Steels the most competitive alternative for cold formed and welded products.

Domex 500 MC with designation D and E meet and exceed the demands for steel S500 MC in EN-10149-2.

Applications

The extra high strength steel grades are used in applications such as truck chassis, cranes and earthmoving machines. In these applications, the high strength of the steels is used to save weight and/or to increase the payload.

As a result of this and the good formability of the steels, the total costs can be reduced.

Dimension range

Domex 500 MC is available in the range of sizes tabulated below in as rolled or pickled condition with mill edge.

For material with trimmed edges, the width is reduced by 35 mm.

Some exceptions may occur.

Thickness (mm)	Width (mm)	Length (mm)
2,00 - (3,00)	1000 - 1035	1500 - 13000
3,00 - (3,50)	885 - 1350	1500 - 13000
3,50 - (4,00)	885 - 1400	1500 - 13000
4,00 - (5,00)	885 - 1500	1500 - 13000
5,00 - (10,00)	885 - 1600	1500 - 13000
10,00 - (11,00)	885 - 1400	1500 - 13000
11,00 - 12,00	885 - 1300	1500 - 13000

Chemical composition

C	Si	Mn	P	S	Al	Nb	V	Ti
%	%	%	%	%	%	%	%	%
max	max	max	max	max	min	max	max	max
0,10	0,10 ¹⁾	1,60	0,025	0,010	0,015	0,09 ²⁾	0,20 ²⁾	0,15 ²⁾

1) If the material is to be hot-dip galvanized, this must be specified in the order.

2) Sum of Nb, V and Ti = 0.22% max.

Mechanical properties

Yield strength R_{eH} N/mm ² min	Tensile strength R_m N/mm ² min - max	Elongation on failure	
		< 3 mm A_{80} % min	≥ 3 mm A_5 % min
500	550 - 700	14	18

Bendability

	Nominal sheet thickness, t		
	≤ 3 mm	3 mm < t ≤ 6 mm	> 6 mm
Min. recommended bending radius (≤ 90°)	0,6 x t	0,8 x t	1,0 x t

Impact strength

The Charpy V-notch test is carried out according to EN 10045-1.

Designation	Test temperature	Energy level
B	Not impact tested	
D	-20°C	40J
E	-40°C	27J

1) Other test temperatures and impact strengths are available subject to special agreement.

Welding

The low contents of carbon, phosphorus and sulphur enable all conventional welding methods to be readily used for Domex 500 MC. No preheating is necessary.

There are a large number of filler metals that can be used for welding of Domex 500 MC,

which gives a weld that can meet the same minimum tensile strength requirements as the base metal. Some examples of different filler metals that can be used are tabulated below.

Heat treatment

Stress relief annealing should be carried out within the temperature range of 530 - 580°C. Heat treatment above this range, e.g. normalizing and hot forming, reduces the strength and should be avoided.

Technical service and information

Knowledge Service Center will be pleased to assist with additional information concerning this product and other products from SSAB Tunnpåt.

Examples of different matching and over matching filler metals

Manual metal arc welding coated electrode	Gas shielded metal arc welding		Submerged arc welding Wire / powder	Manufacturer
	Cored electrode	Wire electrode		
OK 74.78 Filarc 88 S P 48 S, Maxeta 21 Tenacito 70	OK Tubrod 15.17 Filarc PZ6145 DWA 50, DWA 55E Fluxofil 41	OK Autrod 12.51 Filarc PZ6041; PZ6047 Elgamatic 103 Carbofil CrMo-1	OK 12.24/OK Flux 10.62 - - Fluxocord 41/Powder OP 121TT	ESAB Filarc ELGA Oerlikon

The particulars in this data sheet are correct at the time of going to print and are intended to give general guidance for the use of the product. Subject to changes arising from continual product development. The information and data must not be regarded as guaranteed values, unless specially confirmed in writing.

SSAB Tunnpåt AB
SE-781 84 Borlänge
Sweden
Tel +46 243 700 00
Fax +46 243 720 00
office@ssabtunnplat.com
ssabtunnplat.com
ssabdirect.com

Denmark
SSAB Svensk Stål A/S
Tel +45 4320 5000
ssab.dk

Finland
OY SSAB Svenskt Stål Ab
Tel +358-9-686 6030
ssab.fi

France
SSAB Swedish Steel SA
Tel +33 1 55 61 91 00
ssab.fr

Germany
SSAB Swedish Steel GmbH
Tel +49 211 91 25-0
Tel +49 711 6 8784-0
ssab.de

Great Britain
SSAB Swedish Steel Ltd
Tel +44 1905 795794
swedishsteel.co.uk

Italy
SSAB Swedish Steel S.p.A
Tel +39 030 905 881 1
ssab.it

The Netherlands
SSAB Swedish Steel BV
Tel +31 24 67 90 550
ssab.nl

Norway
SSAB Svensk Stål A/S
Tel +47 23 11 85 80
ssab.no

Poland
SSAB Swedish Steel Sp z o.o.
Tel +48 22 723 04 80

Portugal
SSAB Swedish Steel
Tel +351 256 371 610
ssab.pt

Spain
SSAB Swedish Steel S.L.
Tel +34 91 300 5422
ssab.es

USA
SSAB Swedish Steel Inc.
Tel +1 412-269 21 20
swedishsteel.us

Brazil
SSAB Swedish Steel Ltda.
Tel + 55 41 3014 9070
ssab.com.br

South Africa
SSAB Swedish Steel Pty Ltd
Tel +27 11 822 2570
swedishsteel.co.za

China
SSAB Swedish Steel
Tel +86 10 6466 3441
swedishsteel.cn

Korea
SSAB Swedish Steel Ltd
Tel +82 31 906 2770